



HDPE CD4625

High Density Polyethylene Pipe Resin

PIPE

RESIN PROPERTIES ⁽¹⁾

	Method	Unit	Typical Value
Melt Flow Index	D1238	g/10 min	–
190°C/2.16 kg	–	–	0.3
190°C/21.6 kg (HLMI)	–	–	23
Density	D792	g/cm ³	0.946
Melting Temperature	D3418	°F	268

MECHANICAL PROPERTIES ^{(1) (2)}

	Method	Unit	Typical Value
Tensile Strength at Yield	D638	psi	3,200
Elongation at Break	D638	%	> 600
2% Flexural Modulus (Sec)	D790	psi	110,000
Shore Hardness, D Scale	D2240		63
ESCR (10% Igepal, F10 condition B)	D1693	hrs	>1000

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

(2) The data listed were determined on compression-molded specimens and may, therefore, vary from specimens taken from molded articles.

(3) When CD4625 is blended with a carbon black masterbatch that results in a 2% to 4% level of carbon black in the final conduit or a colored masterbatch containing UV additives that results in outdoor storage protection of at least one year, the resulting material used in the production of conduit will meet or exceed the minimum cell classification of PE334480C or PE334480E, respectively, as required in standards ASTM F2160, UL 651A, and NEMA TC-7.

CHARACTERISTICS:

- Multimodal enhanced resin made with Borstar®3G Technology
- Excellent processing and melt strength
- Outstanding stress crack resistance
- Meets material requirements for ASTM F2160⁽³⁾

APPLICATIONS:

- Profile extrusion
- Conduit
- Corrugated pipe

All tests were run under laboratory conditions using American Society for Testing and Materials standards (where applicable) or internal testing procedures. The data is offered in good faith but is intended as a general guide only, and does not necessarily represent results that may be obtained elsewhere. The use of Bayport Polymers LLC ("Baystar") products must be guided solely by the user's own methods for selection of proper formulation to ascertain fitness for any specific application. Baystar disclaims any responsibility for misuse or misapplication of its products and the user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained in the data or the use of the product. The data is provided without reference to any intellectual property issues, as well as federal, state, or local laws which may be encountered in the use thereof. BAYSTAR MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. Baystar's liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited, at customer option, to replacement of nonconforming goods or refund not to exceed the purchase price plus transportation charges thereon in respect to any material subject to a claim. In addition to any prohibitions of use (if any), Baystar may further prohibit or restrict the sale of its products into certain applications. For further information, please contact your Baystar representative. All products supplied by Baystar are subject to its standard terms and conditions set out in the contract or applicable purchase order. Baystar is a registered trademark of Bayport Polymers LLC. Borstar is a registered trademark of Borealis AG. This document may not be distributed, displayed (in any form including a website), copied, altered, or reproduced in whole or in part without Baystar's prior written authorization. To the extent Baystar specifically authorizes distributing, displaying and/or copying this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information.

